

BALLISTIC TEST REPORT

DATE: 13/02/2013

REPORT NO.: 130112

CUSTOMER: HAGOR		PRODUCT: _____	
Shell NO. : _____			
PANEL TYPE PE Helmet Shell		TEST STD. NIJ STD. 0101.04 IIIA	
PASGT		Distance 5 [m]	
Sell Weight [kg] 0.85	Thick. [mm] 7.5	TEMP. 20 [C°]	
		Relative Humidity 43 [%]	
Remarks: _____ _____ _____			

TEST REPORT

Clay Calib. [mm]	1	2	3	4	5	AVG.
	19.9	20.1	20	20.2	19.8	20

Test No.	Barrel Diameter [mm]	Round		Bullet		Velocity [m/s]	Velocity [ft/s]	Back Face [mm]	Stop / Penetrate	Shot Angle	Remarks
		Type	Lot	Type	Weight [grain]						
1	9	LUGER (PB)	REM	FMJ	124	436.17	1,431	5.4	STOP	0	Rear
2	9	LUGER (PB)	REM	FMJ	124	435.56	1,429	5	STOP	0	Left
3	9	LUGER (PB)	REM	FMJ	124	437.69	1,436	5.2	STOP	0	Front
4	9	LUGER (PB)	REM	FMJ	124	436.78	1,433	5.6	STOP	0	Right
5											
6											
7											
8											
9											
10											
11											
12											

Remarks:

Approved by: **Yaniv Montakyo**
VP R&D
Head of Ballistic Laboratory